

RECOMMENDED CUTTING CONDITIONS

Drill Dia. DC		Mild Steel ($\leq 180\text{HB}$)			Carbon Steel, Alloy Steel (180–280HB)		
		AISI 1010 etc.			AISI 1045, 4140 etc.		
inch	mm	Cutting Speed (Min.—Max.) (SFM)	Feed (Min.—Max.) (IPR)	Peck (inch)	Cutting Speed (Min.—Max.) (SFM)	Feed (Min.—Max.) (IPR)	Peck (inch)
.00394	0.10	20 (15–25)	.0001 (.00004–.0001)	.0008	20 (15–25)	.0001 (.00004–.0001)	.0008
.00472	0.12	25 (15–35)	.0001 (.00004–.0001)	.0008	25 (15–35)	.0001 (.00004–.0001)	.0008
.00630	0.16	35 (20–45)	.0001 (.00004–.0001)	.0008	35 (20–45)	.0001 (.00004–.0001)	.0008
.00787	0.20	40 (25–50)	.0001 (.0001–.0002)	.0016	40 (25–50)	.0001 (.0001–.0002)	.0016
.00984	0.25	50 (35–65)	.0001 (.0001–.0002)	.0016	50 (35–65)	.0001 (.0001–.0002)	.0016
.01260	0.32	65 (45–85)	.0002 (.0001–.0002)	.0020	65 (45–85)	.0002 (.0001–.0002)	.0020
.01575	0.40	80 (50–105)	.0002 (.0001–.0002)	.0020	80 (50–105)	.0002 (.0001–.0002)	.0020
.01969	0.50	105 (65–115)	.0002 (.0002–.0003)	.0039	105 (65–115)	.0002 (.0002–.0003)	.0039
.02480	0.63	130 (80–150)	.0003 (.0002–.0004)	.0039	130 (80–150)	.0003 (.0002–.0004)	.0039
.03150	0.80	165 (115–195)	.0008 (.0006–.0010)	.0118	165 (115–195)	.0006 (.0005–.0007)	.0118
.03937	0.99	205 (130–230)	.0016 (.0012–.0020)	.0118	205 (130–230)	.0008 (.0006–.0010)	.0118

Drill Dia. DC		Carbon Steel, Alloy Steel (280–350HB)			Pre-hardened Steel		
		AISI 4340 etc.			AISI P21, P20 etc.		
inch	mm	Cutting Speed (Min.—Max.) (SFM)	Feed (Min.—Max.) (IPR)	Peck (inch)	Cutting Speed (Min.—Max.) (SFM)	Feed (Min.—Max.) (IPR)	Peck (inch)
.00394	0.10	20 (15–25)	.0001 (.00004–.0001)	.0008	20 (15–25)	.0001 (.00004–.0001)	.0008
.00472	0.12	25 (15–35)	.0001 (.00004–.0001)	.0008	25 (15–35)	.0001 (.00004–.0001)	.0008
.00630	0.16	35 (20–45)	.0001 (.00004–.0001)	.0008	35 (20–45)	.0001 (.00004–.0001)	.0008
.00787	0.20	40 (25–50)	.0001 (.00008–.0002)	.0016	40 (25–50)	.0001 (.00008–.0002)	.0016
.00984	0.25	50 (35–65)	.0001 (.00008–.0002)	.0016	50 (35–65)	.0001 (.00008–.0002)	.0016
.01260	0.32	65 (45–85)	.0002 (.00012–.0002)	.0020	65 (45–85)	.0002 (.00012–.0002)	.0020
.01575	0.40	80 (50–105)	.0002 (.00012–.0002)	.0020	80 (50–105)	.0002 (.00012–.0002)	.0020
.01969	0.50	105 (65–115)	.0002 (.00020–.0003)	.0039	105 (65–115)	.0002 (.00020–.0003)	.0039
.02480	0.63	130 (80–150)	.0003 (.00024–.0004)	.0039	130 (80–150)	.0003 (.00024–.0004)	.0039
.03150	0.80	165 (115–195)	.0006 (.00047–.0007)	.0118	165 (115–195)	.0006 (.00047–.0007)	.0118
.03937	0.99	205 (130–230)	.0008 (.00059–.0010)	.0118	205 (130–230)	.0008 (.00059–.0010)	.0118

Drill Dia. DC		Austenitic Stainless Steel ($\leq 200\text{HB}$)			Gray Cast Iron ($\leq 350\text{MPa}$)		
		AISI 304, 316 etc.			No45B etc.		
inch	mm	Cutting Speed (Min.—Max.) (SFM)	Feed (Min.—Max.) (IPR)	Peck (inch)	Cutting Speed (Min.—Max.) (SFM)	Feed (Min.—Max.) (IPR)	Peck (inch)
.00394	0.10	20 (15–25)	.0001 (.00004–.0001)	.0008	20 (15–25)	.0001 (.00004–.0001)	.0008
.00472	0.12	25 (15–35)	.0001 (.00004–.0001)	.0008	25 (15–35)	.0001 (.00004–.0001)	.0008
.00630	0.16	35 (20–45)	.0001 (.00004–.0001)	.0008	35 (20–45)	.0001 (.00004–.0001)	.0008
.00787	0.20	35 (20–45)	.0001 (.00008–.0002)	.0016	40 (25–50)	.0001 (.00008–.0002)	.0016
.00984	0.25	45 (25–60)	.0001 (.00008–.0002)	.0016	50 (35–65)	.0001 (.00008–.0002)	.0016
.01260	0.32	50 (35–65)	.0002 (.00012–.0002)	.0020	65 (45–85)	.0002 (.00012–.0002)	.0020
.01575	0.40	50 (35–60)	.0002 (.00012–.0002)	.0020	80 (50–105)	.0002 (.00012–.0002)	.0020
.01969	0.50	50 (35–65)	.0002 (.00020–.0003)	.0039	105 (65–115)	.0002 (.00020–.0003)	.0039
.02480	0.63	50 (35–65)	.0003 (.00024–.0004)	.0039	130 (80–150)	.0003 (.00024–.0004)	.0039
.03150	0.80	50 (35–65)	.0006 (.00047–.0007)	.0079	165 (115–195)	.0008 (.00059–.0010)	.0118
.03937	0.99	50 (35–65)	.0008 (.00059–.0010)	.0079	205 (130–230)	.0016 (.00118–.0020)	.0118

Drill Dia. DC		Aluminium Alloy (Si<5%) ASTM A6061, A7075 etc.			Heat Resistant Alloy Inconel718 etc.		
		Cutting Speed (Min.—Max.) (SFM)	Feed (Min.—Max.) (IPR)	Peck (inch)	Cutting Speed (Min.—Max.) (SFM)	Feed (Min.—Max.) (IPR)	Peck (inch)
inch	mm						
.00394	0.10	20 (15—25)	.0001 (.00004—.0001)	.0020	5 (5—15)	.00004 (.00002—.00004)	.0008
.00472	0.12	25 (15—35)	.0001 (.00008—.0002)	.0020	10 (5—15)	.00004 (.00002—.00004)	.0008
.00630	0.16	35 (20—45)	.0002 (.00012—.0002)	.0020	15 (10—20)	.00004 (.00002—.00004)	.0008
.00787	0.20	40 (25—50)	.0002 (.00020—.0003)	.0039	15 (10—20)	.00008 (.00004—.00008)	.0016
.00984	0.25	50 (35—65)	.0003 (.00024—.0004)	.0039	15 (10—20)	.00008 (.00004—.00008)	.0016
.01260	0.32	65 (45—85)	.0004 (.00031—.0005)	.0118	15 (10—20)	.00008 (.00004—.00008)	.0020
.01575	0.40	80 (50—105)	.0008 (.00059—.0010)	.0118	15 (15—20)	.00008 (.00004—.00008)	.0020
.01969	0.50	105 (65—115)	.0012 (.00098—.0014)	.0197	15 (15—35)	.00012 (.00004—.00012)	.0039
.02480	0.63	130 (80—150)	.0016 (.00138—.0018)	.0197	20 (15—35)	.00016 (.00008—.00016)	.0039
.03150	0.80	165 (115—195)	.0020 (.00177—.0022)	.0315	20 (15—35)	.00024 (.00016—.00024)	.0079
.03937	0.99	205 (130—230)	.0024 (.00217—.0026)	.0315	20 (15—35)	.00039 (.00031—.00039)	.0079

(Note 1) You must use the MSP starter drill when using the MSE drill.

(Note 2) Change cutting conditions depending on your machine and workpiece rigidity.

(Note 3) When machining holes over 5DC, reduce the step stated above.

(Note 4) The use of water-soluble fluid (diluted by 20 times) is recommended for drilling under the cutting conditions above. Lower the revolutions if you use oil fluid or mist.

(Note 5) For the spindle revolution of diameters not shown in the table, please adjust to the conditions of larger and closest diameter, or calculate from the cutting speed of the closest diameter. For the feed rate per revolution, please set up within the recommended feed rate of the closest diameter appropriately.